

TECHNIKAI ADATLAP

DakerFoam habosított PVC lemez

ASTM test	Property	Rigid	Flexible
PHYSICAL			
D570	Water absorption, 24 hours, 1/8 inch thick (%)	0.04-0.4	0.15-0.75
THERMAL			
C177	Thermal conductivity (10~4 cal-cm/sec-cm~2-°C)	3.5-5.0	3.0-4.0
D696	Coefficient of thermal expansion (10~5 in./in.-°F)	1.2-5.6	3.9-13.9
ELECTRICAL			
D149	Dielectric strength (V/mil) short time, 1/8-in. thick	350-500	300-400
D150	Dielectric constant At 1kHz	3.0-3.8	4.0-8.0
D150	Dissipation factor At 1kHz	0.009-0.017	0.07-0.16
D257	Volume resistivity (ohm-cm) At 73°F, 50% RH	>10~16	10~11 to 10~15
D495	Arc resistance(s)	60-80	-

Méret táblázat

Vastagság	Tábla méret			Szín	Tábla mennyiség
mm	1220x3050	1560x3050	2050x3050		raklaponként
1	x	x	x	szín	450/350/275
2	x	x	x		225/175/125
3	x	x	x		150/125/100
4	x	x	x		125/100/75
5	x	x	x		100/75/50
8	x	x	x		55/45/35
10	x	x	x		45/35/25
12	x	x			35/30
15	x	x			30/25
19	x	x			25/20