

## PP Sheets

### ViPrint™ Pure Glass 3800

#### Product Datasheet

### AXPRINT® Pure Glass

Version 4 01/12/2011

#### Description

VitasheetGroup's ViPrint Polypropylene sheets are designed for the graphic arts industry. They are corona treated on both sides and can be printed and decorated using different techniques (Screen or offset printing, embossing, hot foil stamping). They include an antistatic treatment to avoid attracting dust. They are offered in a wide range of colours and emboss finish and are often available from stock.

ViPrint Pure Glass 3800 is a printable range with a unique transparency. Its characteristics include very high quality, high transparency and anti-blocking.

#### Applications

Luxury packaging and clear boxes.

#### Key Features

##### Certification/Approvals

Approved grades (depending on colour) are available on request.

Food: Commission Regulation (EU) N°10/2011

TOY: EN 71 Part 3.

##### Printing

Screen or offset printing (please specify).

#### Product Availability

##### Colour

Transparent clear

##### Finish

Gloss / Gloss G03.

##### Thickness

Ⓝ 0.40 mm to 0.70 mm.

##### Minimum Order Quantity

1000Kg per size/ thickness/ colour

on a minimum production campaign of 3 tons G03

#### Sheet Size Specifications

Gauge	Width	Length
0.40 to 0.70 mm	500/800 mm	700/1200 mm

NB: available sizes may vary depending on colours/embosses/order size.  
Please contact our sales department.

Properties	Value
Density 0.400mm	0.93
Density ≥ 0.410mm	0.92

## Additional Information

### Conversion

~~Guillotine cutting: Can be cut on traditional printing guillotine with double-edged blade.~~

Creasing: Cold and hot creasing techniques can be used depending on the thickness. The resulting hinges can be folded millions of times thanks to the remarkable characteristics of polypropylene.

Welding: Different techniques can be used to weld ViPrint (Thermal (thin gauge) and Ultrasonic).

Gluing: ViPrint can be glued with PUR glue.

### Thermoforming

This product is not recommended for thermoforming.

### Outdoor/UV Resistance

In outdoor or strong UV light conditions, ViPrint can become brittle in a matter of months. For UV resistance grades please contact the Sales Office.

### Storage

This product has been corona treated which is required to allow ViPrint to be printed and glued. It should be noted that it has a limited shelf life, which can be effected by how it is stored. Ideally it should be stored in dark, dry and cool conditions.

## Manufacturing Tolerances

	Up to 0.8 mm
Gauge	± 0.02 mm
Length*	± 1.5 mm
Width*	± 1 mm

\* Maximum difference between 2 sheets of a same lot.

**VitasheetGroup**  
Charta House  
30 - 38 Church Street  
Staines  
TW18 4EP  
United Kingdom  
[www.vitasheetgroup.com](http://www.vitasheetgroup.com)

**Carolex Graphic Arts Dpt.**  
Zone industrielle  
62620 RUITZ  
France  
tel : + 33 3 21 61 66 66  
[graphic.arts@vitasheetgroup.fr](mailto:graphic.arts@vitasheetgroup.fr)