

| | Unit | Value | | Test Method |
|----------------------------|-------------|--------------|-----|--------------------|
| Yarn | Denier | 300DX500D | | DIN60001 |
| Construction | Thread/Inch | 18X12 | | DIN53853 |
| Base Fabric Weight | g/sqm | 65 | | DIN53352 |
| PVC Coating Weight | g/sqm | 375 | | DIN53352 |
| Finished Product Weight | g/sqm | 440(±10) | | DIN53352 |
| Finished Product Thickness | mm | 0.38 (±0.02) | | DIN53353 |
| Specification | m | 1.02-5 | | ----- |
| Tensile Strength | N/5cm | MD | 634 | DIN53354 |
| | | TD | 759 | |
| Elongation at break | % | MD | 15 | DIN53354 |
| | | TD | 13 | |
| Tearing Strength | N/5cm | MD | 205 | DIN53363 |
| | | TD | 232 | |
| Peeling Strength | N/5cm | 37 | | DIN53357 |
| Translucent | % | 15 | | ASTM D 1003 |
| Temperature resistance | °C | -30°C+70°C | | DIN53372 |