

NANO-TACK TRANSPARENT PET
155 micron

Item	Description	Specification
Composition	Product Code and packaging	NANO-PET1550-13 1,37*50m
	Type of support	PET biaxial film
	Finish	Clear transparent coated
	Layers	Front Layer: clear gloss PET film 155 my
		Liner: PET film 50 micron
Total thickness & weight	Back treatment: 25 my silicon suction cups Total thickness 180 my ± 10 (235 gsm± 10)	
Technical data	Elongation at Break (ASTM D638 M89 - %)	> 80%
	Release force	< 0.09 N/25mm
	Peeling force (24h)	0.02 ≥ x ≤ 0.1 N/25mm
	Dimensional Stability (MD)-(ASTM D1204-02)	≤ 0.1 in
	Surface Tension (ASTM D2578-04°)	32 ÷ 36 dyne/cm
	Working temperature	- 40 °C ÷ 120 °C
	Application temperature	8 ÷ 30 °C
Application	<p>The product is designed for all kinds of flat, clean and gloss surfaces (glasses, vehicles, screens, furniture, metal, etc.). Mounting conditions: temperature not less than 8°C, no more than 30°C. For more information: ask for the brochure with all the hints. Sun exposure (European weather conditions): the average time of exposure is 8 - 12 months. Notes: it is obviously very important that the surface on which you are going to apply the product is appropriately cleaned, as required for any kind of applications.</p>	
Storage Period	12 months under ordinary conditions at the mean temperature of 23 ± 2°C (min. 12°C, max. 25°C) and relative humidity of 50 - 70%. A high storage temperature and humidity may decrease the ink absorption.	
Printing Compatibility	<p>- Suitable for screen and digital printing. - Suitable for UV Curable, Latex inks. For eco-solvent inks, before starting the print operation, make sure the linearization on the RIP, is fixed in accordance with the specifics of the printer on which you want to print the PET media (ink limit 100-130%) and the evaporation and curing of the ink is completed. Note: best printing conditions: 16-28°C, humidity 30-60%, atmospheric pressure 1004÷1025 hPa Notice: when realizing saturated images, the die cutting at the edges of the printed image has to be avoided; it would be better to leave an edge of a few millimeters from the printed area, to prevent the image edges from curling. Anyway, if you cut the printed areas, it is highly recommended that the ink drying process is completed, that is, be aware that the ink is totally dried or cured before cutting the selvages. Notes: due to the wide number of ink producers and digital printing machines, weather conditions and printing variability, tests before printing are recommended.</p>	
REACH Regulation	Complying with the Italian Decree-Law n. 133 issued on 14.09.2009 and published on the Italian <i>Gazzetta Ufficiale</i> , we inform that no phthalates are present in the product. For further information, please refer to the certified copy available of the analyses worked out on the substances taken into consideration by REACH (Registration Evaluation Authorization of Chemicals).	
Notes	<p><i>Published information is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of the products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to changes without prior notice.</i></p>	

